




# CAPACOLOR

POLYMER MODIFIED TILE JOINT GROUT FOR  
JOINT WIDTH 0 TO 4 MM.

- Attractive colours
- Water resistant
- Low shrinkage
- High mechanical performance

REV\_03/26

CAPACOLOR



## DESCRIPTION

**CAPACOLOR** is a cementitious polymer grout with special additives and resistant inorganic pigments, used to fill joints 0 - 4 mm wide and suitable for filling joints between any ceramic and natural stone tiles.

## JOINT GROUTING

- Existing surfaces in tiles/stones
- Ceramic/Vitrified tiles
- Glass mosaic
- Natural Stones/marbles/granites
- Engineered/manufactured stones/marbles
- Sensitive/rough tiles/stones/marbles

## APPLICATION AREAS

- Internal & external use
- Wall/floor
- Bathroom
- Swimming pool
- Water Tanks
- Residential and Commercial applications

## PACK

1 Kg Mini Pack

## WATER DOSAGE

260 to 310 ML

## SHELF LIFE

12 months in original  
unopened packing

## COLOUR

20+ shades



EN ISO 14025

## APPLICATION STEPS



Remove the hardened adhesive/cement slurry/mortar and plastic spacers from joints using mechanical tools.

.....



Clean the joint with air blower and make the joints dust free.

.....



Add **Capacolor** in bucket containing water and mix with mechanically operated mixer to obtain a mixture of homogeneous creamy consistency.

.....



Fill and press the mixture in tile joints with rubber spatula with filling in diagonal passion and remove excess grout from surfaces. Wait to set the grout for few minutes and begin cleaning application.

.....



Clean the total surface area using wet sponge with following circular passion and remove all excess particles from surfaces.

## RECOMMENDATIONS

- Detergent wash must be completed at least 10 days prior to actual grout application, if its required.
- Block the access to other agencies like false ceiling/POP/furniture/painting during grout application.
- At least 24 hrs must be left blocked the area to set the grout and reflect original selected shade.
- Grout must be filled minimum twice of the joint width for longer stability.

## DO NOT USE

- Addition of other ingredients which may alter final performance of the product.
- On stagnant water

## WORKABILITY PERFORMANCE

Recommended width (mm)	From 0 to 4
Consistency	Creamy paste
Appearance of mixture	Pre mixed powder
Mixture density (kg/dm <sup>3</sup> )	1.8±0.05
Coverage (Kg/sq.m)	Refer coverage chart
Temperature of surfaces and materials (°C)	From +1 to +40
Pot life (min)	≥ 60
Grout application in joints	24 hrs for wall and floor
Foot traffic	Light foot traffic > 24 hrs Heavy foot traffic > 7 days Swimming pool > 14 days

at 23±2 °C, 50±5% RH and no ventilation

## TECHNICAL PERFORMANCE

EN 13888	Requirements of CG2 WA	Results	Classification
Compressive strength after 28 days (Mpa)	> 15	≥ 25	Type CG2 W
Flexural strength after 28 days (Mpa)	> 2.5	> 4	
Water absorption after 30 mins (g)	< 2	< 1	
Water absorption after 240 mins (g)	< 5	< 2	
Shrinkage (mm/M)	< 3	< 0.08	
Abrasion resistance (mm <sup>3</sup> )	< 1000	< 850	

at 23±2 °C, 50±5% RH and no ventilation

## COVERAGE FORMULA

$$R = 1,82 \times Z \times H \times (10/Z + 10/Y).$$

R = Covergae: kg/m<sup>2</sup>

Z : Joint Width in cm

H : Joint Depth in cm

X : Tile Width in cm

Y : Tile Length in cm

1.82 : Paste density (kg/l)

## COLOR CHART

	01. BLANCO		11. DOVE GREY
	02. GREY		12. LIMESTONE
	03. DARK GREY		13. ARGENT SILVER
	04. ANTHRACITE		14. TWILIGHT
	05. JET BLACK		15. MOCHA
	06. BAHAMA BEIGE		16. FERROUS GREY
	07. CARAMEL		17. JAISALMER
	08. BROWN		18. TERACOTTA
	09. WALNUT		19. SEA BLUE
	10. IVORY		20. KOTA GREEN

Note: While every precaution is taken during printing, the exact matching of the colors/shades cannot be guaranteed. Shades shown here are for indicative purpose only.

Disclaimer: While our tile adhesive is formulated to adhere to industry standards and recommended application methods, we cannot be held responsible for any misuse, improper application, or deviation from our provided guidelines. It is essential to follow the prescribed instructions and use the product within its intended purpose for optimal results. Any alternative use or application outside our guidelines is done at the user's own risk.

### INTERNATIONAL COMBUSTION (INDIA) LIMITED

#### REGISTERED OFFICE:

Infinity Benchmark, 11th Floor, Plot No. G-1  
Block EP & GP, Sector V, Salt Lake  
Kolkata - 700 091, West Bengal, India  
Phone: +91 (033) 4080 3000  
E-mail: [info@capaindia.in](mailto:info@capaindia.in)

[www.capaindia.in](http://www.capaindia.in)

#### WORKS:

Plot No. B 300, Ajaymeru Palra  
RIICO Industrial Area,  
Ajmer - 305025, Rajasthan, India  
Phone: +91 (0145) 2970337

For any assistance and complaints, contact  
[info@capaindia.in](mailto:info@capaindia.in)



**STRONGER TOGETHER**