



SUPERCAPA

HIGH-PERFORMANCE CEMENT-BASED TILE ADHESIVE C1TE

Highly moisture-resistant adhesive, for laying ceramic tiles of medium / high / low porosity, both indoors and outdoors. High adhesive strength. Particularly recommended for vitrified tiles/glass mosaic tiles in swimming pools.

- Good workability
- Non-slip, extended open time
- High moisture resistance

DESCRIPTION

SUPERCAPA is cement-based adhesive, classified as C1TE in accordance with Standard UNE-EN 12004 and ISO 13007. Adhesive with a guaranteed high bond strength and excellent moisture resistance as a result of the quality of its hydraulic bonding materials. The technology used in Supercapa C1TE adhesive gives the product good rheological characteristics, as well as reduced slip, as a result of the copolymers incorporated in the mixture.

APPLICATION SURFACES

Conventional surfaces and cement-based mortar floors and finishes. The application surface must be hard, perfectly set and free from dust, paint, oil, etc.

INSTRUCTIONS FOR USE



- 1 Add water and mix by hand or mechanically until you obtain a smooth paste of a workable consistency.
- 2 Leave the paste to stand for 5 minutes and mix again before applying.
- 3 Spread the paste on the surface in sections of a surface area no larger than 2 m², combing with a suitable trowel. If double gluing is required, spread the mixture over the back of the tile as well.
- 4 Put the ceramic tiles on top of the freshly-laid adhesive, pressing lightly to ensure that the whole tile surface comes into contact with the adhesive, filling any grooves.
- 5 Leave a joint of a width of at least 2 mm between indoor tiles and at least 5 mm between outdoor tiles. Wait 24 hours before grouting wall tiles and 48 hours before grouting floor tiles.
- 6 Respect all perimeter and structural joints. Place one partition joint every 50 m² for indoor floor tiling, and one every 30 m² for outdoor floor tiling.

APPLICATIONS

Tiling indoor floors and finishes and outdoor floors using ceramic tiles of medium/high/low porosity. A double glue technique should be used for tiles larger than 900 cm² (30 cm x 30 cm). Suitable for use for laying natural stones, vitrified tiles, marbles and fixing glass mosaic tiles.

WARNINGS AND RECOMMENDATIONS

- Avoid applying on dead plaster or weak renderings.
- Do not apply this product when frost or rain are forecasted.
- In extreme weather conditions (wind or high temperatures), the product will dry more quickly than usual. This will result in a shorter open time.
- In high temperatures, windy conditions or if the application surface is very absorbent, it is advisable to moisten the surface and wait for the film of water to disappear before applying the product.
- Check, periodically, that a surface film has not formed on the adhesive paste once it has been spread onto the surface. If a film has formed, remove the product and apply a fresh coat.
- Check that the paste is sticky enough by periodically lifting one of the tiles already in place to ensure that it is well stuck down.
- Use within 1 year of date of packaging. Store the product in its original packaging in a dry, covered place protected from humidity.

SUPERCAPA

HIGH-PERFORMANCE CEMENT-BASED TILE ADHESIVE C1TE

AVAILABLE PACK SIZE

SUPERCAPA is available in 25 kg paper sacks with moisture-proof plastic lining.



TECHNICAL FEATURES

Appearance	White or grey powder	Adhesive strength under normal conditions	$\geq 1.15 \text{ N/mm}^2$
Grain size	$< 0.6 \text{ mm}$	Adhesive strength after water cycle	$\geq 0.5 \text{ N/mm}^2$
Powder density	1.5 kg/l	Adhesive strength after heat cycle	$\geq 0.5 \text{ N/mm}^2$
Paste density	1.7 kg/l	Adhesive strength after freeze/thaw cycling	$\geq 0.5 \text{ N/mm}^2$
Mixing water	6.2-6.6 l/bag	Coverages	1.2-1.3 kg/m ² /mm thickness
Pot life	3 hours	Coming into service at +23°C	Light traffic 1 day Heavy traffic 2 days
Open time	30 minutes	Maximum thickness	15 mm
Adjustment time	30 minutes		
Slip	$\leq 0.5 \text{ mm}$		

Adhesion strength test data is based on per our internal test results

NOTE

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.

REGISTERED OFFICE:

Infinity Benchmark, 11th Floor, Plot No. G-1, Block EP & GP, Sector V
Salt Lake, Kolkata - 700 091, West Bengal, India
Phone: +91 (033) 4080 3000, Fax: +91 (033) 2357 6653, E-mail: info@capaindia.in

WORKS:

Plot No. B 300, Ajaymeru Palra, RIICO Industrial Area, Ajmer - 305025, Rajasthan, India
Phone: +91 (0145) 2970337

www.capaindia.in

Name

Mobile

Email