



aplica Dry

SINGLE-COMPONENT WATERPROOFING MINERAL MORTAR

Waterproofing mortar for a
watertight finishing

- Watertight mortar
- Apply with a trowel or brush
- Use to waterproof swimming pools, terraces...

DESCRIPTION

Mortar made of cements, aggregate, waterproofing polymers and special additives. For indoor and outdoor use. Pressure and counter pressure waterproof.

APPLICATION SURFACES

Concrete, prefabricated concrete blocks and hard, cementrich renderings. The application surface must be hard, perfectly set and free from dust, paint, oil, etc.

INSTRUCTIONS FOR USE



- 1 Add water and mix by hand or mechanically until you obtain a smooth paste of a workable consistency.
- 2 Leave the paste to stand for 5 minutes and mix again before applying.
- 3 Moisten the application surface and apply a thick first coat with a flat brush.
- 4 Leave to dry for 2 to 4 hours.
- 5 Apply a second coat with a flat brush.
- 6 Trowel or smooth the mortar to achieve the desired finishing.
- 7 Wait at least 4 days before filling the tank.

APPLICATIONS

Waterproofing of structures such as swimming pools, terraces, basements, lift shafts, water tanks, retaining walls. To protect buildings from moisture. Foundations, outside walls, terraces, balconies, drains...

WARNINGS AND RECOMMENDATIONS

- Do not apply this product when frost or rain are forecasted.
- Do not apply at temperatures below 5°C or above 35°C.
- To ensure that the mortar provides optimum water resistance, minimum thickness must be of 5 mm.
- In extreme weather conditions (wind or high temperatures), the product will dry quicker than usual. This will result in a shorter open time application.
- In high temperatures, windy conditions or if the application surface is very absorbent, it is advisable to moisten the surface and wait for the film of water to disappear before applying the product.
- Use within 1 year of packaging date. Store the product in its original packaging in a dry, covered place protected from humidity.

aplica Dry

SINGLE-COMPONENT WATERPROOFING MINERAL MORTAR

AVAILABLE FORMATS

aplica Dry is available in 25 kg paper sacks with moisture-proof plastic lining, dispatched on pallets weighing a total of 1,600 kg (64 sacks).



TECHNICAL FEATURES

FEATURES	VALUES
Appearance	White powder
Grain size	< 1 mm
Powder density	1.4 kg/l
Compressive strength 28 days after application	> 25 N N/mm ²
Flexural strength 28 days after application	> 8 N N/mm ²
Paste life	60 minutes
Yield	approx. 8 kg/m ² for thicknesses of 5mm
Reaction to fire	Euroclass A1
Thicknesses	5 - 20 mm

NOTE

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.

REGISTERED OFFICE:

Infinity Benchmark, 11th Floor, Plot No. G-1, Block EP & GP, Sector V
Salt Lake, Kolkata - 700 091, West Bengal, India
Phone: +91 (033) 4080 3000, Fax: + 91 (033) 2357 6653, E-mail: info@capaindia.in

WORKS:

Plot No. B 300, Ajaymeru Palra, RIICO Industrial Area, Ajmer - 305025, Rajasthan, India
Phone: +91 (0145) 2970337

www.capaindia.in

Name

Mobile

Email